



Technical Data

PRODUCT DESCRIPTION

A high performance, two component coating for use where appearance, durability, color and gloss retention plus chemical and corrosion resistance are paramount. For use on automobiles, trucks, trailers, railway cars, service stations, bulk tanks or chemical (acid or caustic) trailers.

For best results, use one of the JONES-BLAIR™ engineered systems for a total coating system.

FEATURES

- Excellent color retention
- Solvent resistant
- Chemical resistant
- Excellent gloss retention
- Lead and Chromate free
- Low VOC

PRODUCT DATA

Description	Results
Vehicle Type	Acrylic Polyester Urethane
Colors	Available in a variety of colors.
Gloss	Full Gloss
VOC (mixed)	394 g/l (3.28 lbs/gal)
Weight/Gallon (mixed)	10 pounds
Solids by Weight (mixed)	67.5%
Solids by Volume (mixed)	54.7% (Theoretical)
Viscosity (mixed)	25" / Zahn 3
Flash Point (white)	48°F
Dry Heat Resistance	300°F (149°C)
Freight Classification	See MSDS
Packaging	1 Gallon (mixed unit)

APPLICATION DATA

Description	Results
Application	Spray
Mix Ratio	3:1 by Volume
Catalyst	99955
Recommended Thickness	1.5 - 3.0 mils DFT
Dry Time @ 77°F, 50% RH	
No Accelerator	
Recoat	3 hours
Tack Free	4 hours
Handle	6 hours
With 1 fl oz/gal 99011	
Recoat	2 hours
Tack Free	2 hours
Handle	5 hours
Pot Life @75°F, 50% RH	
No Accelerator	
2X Viscosity	4 hours
Gel Time	8 hours
With 1 fl oz/gal 99011	
2X Viscosity	2 hours
Gel Time	4 hours

Coverage	582 sf/gal at 1.5 mils DFT
Thinner	21102 (See thinning instructions)
	21092 (See thinning instructions)
	21093 up to 3%
Clean Up	21092

The technical specifications for this data sheet are based on product 45070 White.

CURED FILM PERFORMANCE

Description	Test Method	Results
Q-UV A 340 (3,000 hrs)	ASTM D4587	> 95% gloss retention (60°) color change DE < .5
Xenon Arc (1,000 Hrs) quartz borosilicate filters	ASTM G147-96	> 95% gloss retention (60°)
Exterior Exposure 45° South Dallas, Texas	ASTM D1014	> 90% gloss retention, 3 Years
24 Hour Chemical Resistance Exposure (No Effect)	ASTM 1308	DI Water, 10% H ₂ SO ₄ , 10% NaOH, 25% H ₃ PO ₄ , 10% Acetic Acid, Xylene & Mineral Spirits
Impact Resistance	ASTM D2794	50 F & 20 R
Hardness	ASTM D3363	2H

EQUIPMENT RECOMMENDATIONS

Listed below are general equipment guidelines for the application of this product. Job site conditions may require modifications to these guidelines to achieve the desired results.

SPRAY APPLICATION (General): The following spray equipment has been found suitable and is available from manufacturers such as Binks, DeVilbiss and Graco.

AIR ATOMIZED SPRAY:

	Model	Air Cap	Fluid Tip	Fluid Delivery	Atomizing Pressure
Pressure	Binks #18	63 pb	66	20 oz/min	50 - 55 psi
Pressure	DeVilbiss MBC-510	704	fx	20 oz/min	50 - 55 psi

AIRLESS SPRAY:

Model	Pump Ratio	Fluid Tip	Fluid Pressure	Filter Mesh
Graco Bulldog	30:1	.011 - .013	1800 - 2200	100
Binks B 8D	35:1	.011 - .013	1800 - 2200	100

GENERAL SURFACE PREPARATION

All surfaces must be sound, dry, clean and free of oil, dirt, grease, wax, mildew, loose or flaking paint and other surface contaminants. Remove loose, peeling, flaking or scaling paint and rust by scraping, sanding or wire brush or blasting.

For best results, an SSPC-SP 5 (NACE No. 1) white metal blast is minimum for severe exposure. For moderately severe (non-immersion) exposures an SSPC-SP 6 (NACE No. 3) commercial blast can be used.

DIRECTIONS FOR USE

TINTING: May be tinted with HS tint colors only.

THINNING: This product has been formulated to be applied without the need for additional thinning. However, application with certain equipment and under certain various conditions may be enhanced by reduction with thinners specified. Please note that additional reduction will increase VOC content of the mixed coating. Always know VOC restrictions for coatings applications in your area. This product and other referenced products may not meet VOC restrictions for your application and may not be available in your area.

For products such as 45070, reducer and retarder may be added up to 15% total and remain below Federal VOC restrictions for architectural coatings. For other products such as 45072 Clear, reducer and retarder may be added up to 7% total and remain below Federal VOC restrictions for architectural coatings. Consult the color table or MSDS for details on the VOC levels of the various products. Add 21093 ACRYLITHANE™ Retarder up to 3% to reduce dry spray and orange peel. When temperature is over 70°F, use 21092 ACRYLITHANE™ Reducer. Use ACRYLITHANE™ Fast Spray Reducer for temperatures below 70°F. Pot life is approximately 4 hours after mixing. Mix only the amount of material which can be used within 4 hours. Pot life is decreased with an increase in temperature. Mixed material should be kept in as cool a place as possible. Flush material from pot and lines immediately after use.

APPLICATION: Mix thoroughly before use. Add 1 quart of 99955 per ¾ gallon unit of HS then mix thoroughly again. Only apply when air and surface temperature are between 40° – 100°F (7° - 38°C) and when the surface temperature is at least 5°F or 3°C above the dew point.

DRYING TIME: See application data for typical dry times. Low temperature, high humidity, poor ventilation and thick films will retard drying. Accelerator 99011 may be added at the rate of up to 1 fl oz per mixed gallon of HS to reduce the drying time.

CLEAN UP: Flush mixed material from pot and lines immediately after use. Clean up paint tools or spills immediately with recommended thinner, carefully observing cautions on paint and thinner labels. Dried paint may be removed by scraping.

ENGINEERED SYSTEMS

SYSTEM - A

For maximum corrosion resistance and durability. Recommended for use in coastal and marine exposures above the splash zone over a sandblasted surface.

First coat Primer: 3 dry mils of 33902 CHEM-O-Z™ II Organic Zinc Rich Primer.

Second intermediate coat: 3-5 dry mils of 33304 CHEM-O-PON™ Epoxy Primer or 33010, 33514 or 33114 UREPRIME® HS2.

Topcoat: 3 dry mils of ACRYLITHANE™ HS in the desired color for the finish coat.

Clearcoat: 1 dry mil of ACRYLITHANE™ HS Clear (optional for ultimate gloss and durability).

SYSTEM - B

For maximum chemical resistance while affording excellent corrosion resistance and durability in non-salt atmospheres. Recommended for use in inland areas and for resistance to acid and alkali. Sandblasting is recommended.

First coat Primer – 3 dry mils of 33304 CHEM-O-PON™ Epoxy Primer or 33010 or 33514 or 33114 UREPRIME® HS2.

Topcoat: 3 dry mils of ACRYLITHANE™ HS in the desired color for the finish coat.

Clearcoat: 1 dry mil of ACRYLITHANE™ HS Clear (optional for ultimate gloss and durability).

SYSTEM - C

Recommended for refurbishing existing equipment and structures that have a surface suitable for refinishing by sanding and spot cleanup with hand and power tools.

First coat Primer: 2 dry mils of 33304 CHEM-O-PON™ Epoxy Primer or 33010 or 33514 or 33114 UREPRIME® HS2 (preferred) or 2 mils of 15077 White STANTEST™ Primer or 15632 Gray STANTEST™ Primer.

Topcoat: 2 dry mils of ACRYLITHANE™ HS in the desired color for the finish coat.

Clearcoat: 1 dry mil of ACRYLITHANE™ HS Clear (optional for ultimate gloss and durability).

ALTERNATE PRIMERS: Contact JONES-BLAIR® Company.

HEALTH AND SAFETY

Read the Material Safety Data Sheet (MSDS) and container labels for detailed health and safety information. This product is intended for industrial use by properly trained professional applicators only.

The information, data and suggestions contained herein are believed to be reliable, based upon our knowledge and experience; however, it is expressly declared that Seller does not guarantee the result to be obtained in Buyer's process. **SELLER HEREBY EXPRESSLY DISCLAIMS ANY IMPLIED WARRANTY OF MERCHANTABILITY FOR FITNESS FOR A PARTICULAR PURPOSE AND/OR ANY OTHER WARRANTY, EXPRESS OR IMPLIED** as to any and all products and/or suggestions described herein, whether such products are used alone or in combination with other materials. Buyer must make its own determination of the suitability of any product for its use, and the completeness of any information contained herein. Nothing contained herein shall be construed to constitute inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. 09192006 AcrylithaneHSTD.indd



JONES-BLAIR®

2728 Empire Central - P.O. Box 35286 - Dallas, TX 75235 - Telephone (214) 353-1600 - Fax (214) 350-7624 - www.jones-blair.com